

DECLARATION OF PERFORMANCE

according to Annex III of the Regulation (EU) No 305/2011 of the European Parliament and Construction Products Regulation 2011 (retained EU law EUR 305/2011) as amended by the Construction Products (Amendment etc.) (EU Exit.) Regulation 2019 and the Construction Products (Amendment etc.) (EU Exit) Regulations 2020

No. NH-UK-F-ST-2/05-CPR-25-1

Unique identification code of the product-type:

Hot rolled strip, band and sheet of structural non-alloy steels grade S275J0 according to EN 10025-2, steel number 1.0143

Intended use: Metal structures or in composite metal and concrete structures.

Manufacturer :

NOVÁ HUŤ s.r.o.
Vratimovská 689/117
719 00 Ostrava – Kunčice
Czech Republic
<http://www.novahut.cz>

System/s of AVCP

System 2+

Harmonised / Designated standard:

EN 10025-1:2004

Notified body (EU):

Technický a zkušební ústav stavební
Praha, s.p.
Prosecká 811/76y, Praha 9 -Prosek
No. 1020

Approved body UK:

TUV UK Limited
AMP House
Suites 27-29
Firth Floor
Dingwall Road
Croydon
CR0 2LX
No. 0879

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Ostrava on 9.1.2026

Ing. Aleš Marek

Director of Plant 16 – Downstream Flat

Declared performances				
Basic characteristics	Performance			Harmonised technical specification
Dimensional tolerance	Sheets, strips, stripes		EN 10051	
Yield point (Re)	Nominal thickness (mm)		Values (Mpa)	
	>	≤	min	
		16	275	
Ultimate tensile strength (Rm)	Nominal thickness (mm)		Values (Mpa)	
			min	max
		<3	430	580
	≥3	≤100	410	560
Elongation**	Nominal thickness (mm)		Values (%)	
	>	≤	min. T	min. L
	1	1.5	14	16
	1.5	2	15	17
	2	2.5	16	18
	> 2.5	<3	17	19
	≥3	≤40	21	23
Impact energy	Nominal thickness (mm)		Values (J)	
	>	≤	min	
		150	27 at 0°C	
Weldability CEV	Nominal thickness (mm)		Values (%)	
	>	≤	max	
		30	0.40	
Chemical composition	Nominal thickness (mm)		Values (%)	
	>	≤		
		16	C: 0.18	Cu: 0.55
			Mn: 1.50	N*: 0.012
			P: 0.030	
			S: 0.030	
	* The maximum nitrogen content values do not apply if the total Al content is at least 0.020%, or if other adequate elements that bind N are present. ** Elongation, T – transversal direction, L – Longitudinal direction			