

DECLARATION OF PERFORMANCE

according to Annex III of the Regulation (EU) No 305/2011 of the European Parliament and Construction Products Regulation 2011 (retained EU law EUR 305/2011) as amended by the Construction Products (Amendment etc.) (EU Exit.) Regulation 2019 and the Construction Products (Amendment etc.) (EU Exit) Regulations 2020

No. NH-UK-F-ST-2/15-CPR-25-1

Unique identification code of the product-type:

Hot rolled strip, band and sheet of structural non-alloy steels grade S275J2C according to EN 10025-2, steel number 1.0142

Intended use: Metal structures or in composite metal and concrete structures.

Manufacturer :

NOVÁ HUŤ s.r.o
Vratimovská 689/117
719 00 Ostrava – Kunčice
Czech Republic
<http://www.novahut.cz>

System/s of AVCP

System 2+

Harmonised / Designated standard:

EN 10025-1:2004

Notified body (EU):

Technický a zkušební ústav stavební
Praha, s.p.
Prosecká 811/76y, Praha 9 -Prosek
No. 1020

Approved body UK:

TUV UK Limited
AMP House
Suites 27-29
Firth Floor
Dingwall Road
Croydon
CR0 2LX
No. 0879

This declaratrion of performance is issued, in accordance with Regulation (EU) No 305/2011, as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Ostrava on 9.1.2026

Ing. Aleš Marek

Director of Plant 16 – Downstream Flat

Declared performances					Harmonised technical specification
Basic characteristics	Performance				
Dimensional tolerance	Sheets, strips, stripes		EN 10051		EN 10025-1:2004
Yield point (Re)	Nominal thickness (mm)		Values (Mpa)		
	>	≤	min		
		16	275		
Ultimate tensile strength (Rm)	Nominal thickness (mm)		Values (Mpa)		
			min	max	
		<3	430	580	
	≥3	≤100	410	560	
Elongation**	Nominal thickness (mm)		Values (%)		
	>	≤	min. T	min. L	
	1	1.5	14	16	
	1.5	2	15	17	
	2	2.5	16	18	
	> 2.5	<3	17	19	
	≥3	≤40	21	23	
Impact energy	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		150	27 at -20°C		
Weldability CEV	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0.40		
Chemical composition	Nominal thickness (mm)		Values (%)		
	>	≤			
		16	C: 0.18	Cu: 0.55	
			Mn: 1.50		
			P: 0.025		
			S: 0.025		
	* The maximum nitrogen content values do not apply if the total Al content is at least 0.020%, or if other adequate elements that bind N are present.				
	** Elongation, T – transversal direction, L – Longitudinal direction				